

CMKC6

PRODUCT DATA INFORMATION

ISSUE NO. 3

EFFECTIVE NOV 2005

PAGE 1/1

1. **DESCRIPTION**

CMKC6 Chipfoam is manufactured from combustion modified foam scrap, the crumb foam being bonded together with MDI prepolymer. The rebonded foam has good fatigue properties and can be used in furniture applications to provide a firm feel, or to provide reinforcement in combination with other materials. Other application areas are gym mats, packaging and sound insulation/sound deadening.

2. **TYPICAL PHYSICAL PROPERTIES**

Physical properties are measured using test methods described in the BS4443 series and BS EN ISO 845:1995.

Nominal piece density range 96 ± 10 kg/m³

Nominal tensile strength 50 kPa min.

Nominal compression set 25% max.

3. **FLAMMABILITY CHARACTERISTICS**

Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.

4. **COLOUR**

Standard colour is Orange.

Colours other than the standard colour to be agreed between purchaser and supplier.

PACS reserves the right to update product data information without prior notice.

Issued 05/09/2008