



**PACS**

113 Barkby Road  
Troon Industrial Estate  
Leicester  
LE4 9LG

Telephone (0116) 274 1595

(0116) 276 8555

Fax (0116) 246 1090

Enquiries E-Mail [pacssales@p-a-c-s.co.uk](mailto:pacssales@p-a-c-s.co.uk)

Accounts E-mail [accounts@p-a-c-s.co.uk](mailto:accounts@p-a-c-s.co.uk)

Orders E-mail [orders@p-a-c-s.co.uk](mailto:orders@p-a-c-s.co.uk)

Web Site [www.pacspackaging.co.uk](http://www.pacspackaging.co.uk)

**R390 LD33 Plastazote Polyethylene Foam:**

<i>PROPERTIES</i>	<i>AVERAGE VALUE</i>
Density	33kg m3
Shore Hardness OO Scale	58
Compression set 25% comp 22hr 23 deg C ½ hr recovery 24 hr recovery	10% 3%
Compression Set 50% comp 22hr 23 deg C ½ hr recovery 24 recovery	22.5% 13.5%
Tensile Elongation	155 %
Operating Temperature	- 70°C / + 100°C
Tensile Strength	440 kPa
Tear Strength	785 N/m
Horizontal Burning Characteristics Automotive FMVSS 302 – Burn rate	Pass 7mm and thicker
Horizontal Burn Rate 5mm thick 13mm thick	1.6 mm/sec 1.0 mm/sec

***The above figures are average values.***

***We recommend evaluation prior to use to ascertain the suitability of the material for the application.***