



PACS

113 Barkby Road
Troon Industrial Estate
Leicester
LE4 9LG

Telephone (0116) 274 1595

(0116) 276 8555

Fax (0116) 246 1090

Enquiries E-Mail pacssales@p-a-c-s.co.uk

Accounts E-mail accounts@p-a-c-s.co.uk

Orders E-mail orders@p-a-c-s.co.uk

Web Site www.pacspackaging.co.uk

R430 Stratocell E Specification Sheet

<u>PROPERTIES</u>	<u>TEST METHOD</u>	<u>UNIT</u>	<u>VALUE</u>
DENSITY	DIN 53420	Kg/m ³	24
TENSILE STRENGTH	DIN 53571	N/mm ²	
Extrusion direction			0,219
Cross direction			0,170
ELONGATION AT BREAK	DIN 53571	%	
Extrusion direction			67
Cross direction			52
COMPRESSION STRENGTH	DIN 53577	N/mm ²	
25 % (4th compression)			0,024
50 % (4th compression)			0,081
70 % (4th compression)			0,200
THERMAL STABILITY (24h at 70° C)	ASTM D-3575-S	%	<0,5
CELL SIZE	BS 4443/1 Met.4	Cells/25 mm ≥ 21	
WATER ABSORPTION (after 24 hours)	DIN 53428	Vol %	1,19

The above figures are average values.

We recommend evaluation prior to use to ascertain the suitability of the material for the application.